

A Quality Product from Hawkeye Industries Inc.



Duratec Vinyl Ester Hi-Gloss Topcoat

An easily applied topcoat for tooling and in-mold applications.

Usage

To topcoat patterns, plugs and molds and to topcoat post-painted parts.

Features

You'll get an easily applied, tough durable topcoat, with minimal porosity with Duratec Vinyl Ester Hi-Gloss Topcoat.

Here's why you should choose Duratec Vinyl Ester Hi-Gloss Topcoat—

High HDT—heat distortion temperature of 300 °F, 150 °C.

Easy to apply—sprays quickly.

Resists fisheyes—unique additives reduce the risk of fish-eyes and pinholes during the spray application.

Smooth finish—minimum orange peel.

Hard finish—you'll get a hard, chemical-resistant finish.

High gloss—sands easily and polishes to a non-wax, tack-free high gloss finish.

Duratec Vinyl Ester Hi-Gloss Topcoat

Product Nos.

1904-045 Clear

(Link to MSDS)



Hawkeye Industries Inc.

P O Box 415 Bloomington, CA 92316
Tel 909-546-1160; Toll Free 800-977; Fax: 909-546-1161
Email productinfo@duratec1.com Web www.duratec1.com

Liability/warranty statement: Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.

Duratec is a registered trademark of Dura Technologies Inc.



Product Nos. 1904-045 Clear

Data Sheet
Continued

Duratec Vinyl Ester Hi-Gloss Topcoat

Pg. 2

Duratec Vinyl Ester Hi-Gloss Topcoat Product Properties

All time calculations are based on temperatures of 77° F, 25°C

Viscosity

As measured on a Brookfield Viscometer Model RVF, Spindle #2 at 20 rpm

1000 cps

Thixotropic Index

4+

Gel Time

Sample based on a 100-g mass catalyzed at 2 percent with mekP

12-15 min

Weight per Gallon

8.7 lb

Volatile Organic Compounds

3.36 lb/gal

Link to Application Guides for Duratec Vinyl Ester Hi-Gloss Topcoat

- [Resurfacing Application: Polyester, Vinyl Ester and Epoxy Contact, RTM and Vacuum-Forming Molds](#)
- [Topcoating Application: Wood and MDF Surfaces](#)

Duratec Vinyl Ester Hi-Gloss Topcoat is among the many fine Duratec products marketed worldwide by Hawkeye Industries Inc.

Revised 3-27-05



Hawkeye Industries Inc.

P O Box 415 Bloomington, CA 92316
Tel 909-546-1160; Toll Free 800-977; Fax: 909-546-1161
Email productinfo@duratec1.com Web www.duratec1.com

Liability/warranty statement: Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.

Duratec is a registered trademark of Dura Technologies Inc.